

RECEIVED
CENTRAL FAX CENTER

DEC 15 2006

PTO/SB/97 (09-04)

Approved for use through 07/31/2006. OMB 0831-0031

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.


Certificate of Transmission under 37 CFR 1.8

USPTO Fax No.: (571) 273-8300

I hereby certify that this correspondence is being facsimile transmitted to the United States Patent and Trademark Office

on DECEMBER 15, 2006

Date



Signature

LINDA J. HALLORAN

Typed or printed name of person signing Certificate

302-992-3437

Registration Number, if applicable

Telephone Number

Note: Each paper must have its own certificate of transmission, or this certificate must identify each submitted paper.

10/668892

FA1174USNA

RESPONSE TO NON-FINAL OFFICE ACTION (6 pgs.)

Page 1 of 7

This collection of information is required by 37 CFR 1.8. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.11 and 1.14. This collection is estimated to take 1.0 minutes to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1460, Alexandria, VA 22313-1460.

BEST AVAILABLE COPY

PATENT

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

IN THE APPLICATION OF:

WILLIAM F. GRAHAM ET. AL.

CASE NO.: FA1174USNA

SERIAL NO.: 10/668992

GROUP ART UNIT: 1762

FILED: SEPTEMBER 22, 2003

EXAMINER: WILLIAM F. FLETCHER III

FOR: METHOD FOR ACHIEVING RECOAT ADHESION OVER A FLUORINATED TOPCOAT

AMENDMENT

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Introductory Comments

This is Applicants' response to the Office Action that was mailed on August 23, 2006, for which no shortened period for reply was set. Accordingly, a six (6) month period for a response is in effect.

RECEIVED
CENTRAL FAX CENTER
DEC 15 2006

Application No.: 10/668992
Docket No.: FA1174USNA

Page 2

Amendments to Claims

1. (Withdrawn) A method for in-line or end-of line repair of an original basecoat/topcoat finish on an automobile or truck during their original manufacture, in which the original topcoat comprises a substantially cured fluorinated silane polymer, wherein the improvement comprises:

- (a) incorporating in the original topcoat, an adhesion improving additive comprising a fluorinated urethane compound;
- (b) applying over said original topcoat, a repair basecoat composition comprising an aminoplast resin crosslinking agent;
- (c) applying over said repair basecoat, a repair topcoat composition; and
- (d) curing the new basecoat/topcoat finish.

2. (Withdrawn) The method of claim 1, wherein the repair topcoat is applied over said repair basecoat wet-on-wet and the new top coat and basecoat are cured together.

3. (Withdrawn) The method of claim 1, wherein the coating compositions for both the original basecoat/topcoat and repair basecoat/topcoat are the same, so that only one topcoat and one basecoat composition are used.

4. (Withdrawn) The method of claim 1, wherein the fluorinated urethane compound consists essentially of an adduct of an organic polyisocyanate, a polyoxyethylene/polyoxypropylene glycol, and a fluorinated monofunctional alcohol, and contains substantially no residual isocyanate groups.

5. (Withdrawn) The method of claim 1, wherein the fluorinated urethane compound consists essentially of an adduct of an organic polyisocyanate, an amino-functional silane, and a fluorinated monofunctional alcohol, and contains substantially no residual isocyanate groups.

6. (Withdrawn) The method of claim 1, wherein the fluorinated urethane compound is employed in the original topcoat composition in an amount of about 0.1-10% by weight, based on the weight of the binder of the original topcoat.

BEST AVAILABLE COPY